

[REDACTED]



25X1A

NO. OF PAGES 1

25X1A

NO. OF ENCLS.  
(LISTED BELOW)

SUPPLEMENT TO  
REPORT NO.

DATE OF \_\_\_\_\_

25X1X

1. The rubber gaskets may be described as follows:
2. X-ray diffraction analysis could not be made because of the short elongation but a flame analysis with a copper wire and insolubility in ortho dichlorobenzene indicates the elastomer of all three to be Neoprene. [REDACTED] Note 25X This would be Sovprene<sup>7</sup>
  - a. "O-ring" - A round section rubber gasket of approximately 12 inches diameter.
  - b. "square ring" - A square cross-section rubber gasket of approximately 6 inches diameter.
  - c. "D-ring" - A round section rubber gasket of approximately 2 inches diameter.

3. Results of other tests are:

<u>Sample</u>	<u>% Elongation</u>	<u>Tensile (#/in<sup>2</sup>)</u>	<u>Ash Content</u>
O-ring	160	2020	23.4
Square-ring	185	1740	8.1
D-ring	400	1360	11.1

4. The products have something less than standard physical properties. Tensile strength in our products would be about 3000#. But the gaskets could be expected to render reasonable service.

-end-

**CONFIDENTIAL**

[illegible]